

# 55NT

## EPOXY NONWOVEN ARAMID LAMINATE AND PREPREG



55NT is an epoxy laminate and prepreg system, reinforced with a non-woven aramid substrate. This system combines compatibility with lead-free processing, using a high-temperature epoxy resin, with the low in-plane (X,Y) expansion and outstanding dimensional stability of non-woven aramid reinforcement.



### Features:

- Low in-plane (X,Y) expansion of 6-9 ppm/°C allows attachment of SMT devices with minimal risk of solder joint failure due to CTE mismatch
- Nonwoven aramid organic reinforcement provides outstanding dimensional stability and enhanced registration for improved multilayer yields
- Tg of 170°C, decomposition temperature of 368°C, and Z-expansion of 3.5% between 50-260°C ensures compatibility with most lead-free processes
- Polymeric reinforcement results in PCBs typically 25% lighter in weight than conventional glass-reinforced laminates
- Laser and plasma ablatable for high speed formation of microvias and other features as small as 25µm (µ0.001")
- Electrical and mechanical properties meeting the requirements of IPC-4101/55
- Compatible with lead-free processing

### Typical Applications:

- Military and commercial avionics, missiles and missile defense, satellites, and other high-reliability SMT applications requiring low in-plane (x,y) CTE values
- Other applications requiring low in-plane (x,y) CTE values, including chip carriers and multichip modules, where the chip carrier serves as an interposer for attachment to the underlying PCB
- PCBs that are subjected to elevated temperatures during processing, such as lead-free soldering

**ARLON**  
ELECTRONIC MATERIALS

## Typical Properties:

Property	Units	Value	Test Method
<b>1. Electrical Properties</b>			
Dielectric Constant			
@ 1 MHz	-	3.8	IPC TM-650 2.5.5.3
@ 1 GHz	-		IPC TM-650 2.5.5.9
Dissipation Factor			
@ 1 MHz	-	0.015	IPC TM-650 2.5.5.3
@ 1 GHz	-		IPC TM-650 2.5.5.9
Volume Resistivity			
C96/35/90	MΩ-cm	2.3 x 10 <sup>7</sup>	IPC TM-650 2.5.17.1
E24/125	MΩ-cm	6.6 x 10 <sup>7</sup>	IPC TM-650 2.5.17.1
Surface Resistivity			
C96/35/90	MΩ	1.8 x 10 <sup>8</sup>	IPC TM-650 2.5.17.1
E24/125	MΩ	1.6 x 10 <sup>8</sup>	IPC TM-650 2.5.17.1
Electrical Strength	Volts/mil (kV/mm)	1240 (48.8)	IPC TM-650 2.5.6.2
Dielectric Breakdown	kV		IPC TM-650 2.5.6
Arc Resistance	sec	165	IPC TM-650 2.5.1
<b>2. Thermal Properties</b>			
Glass Transition Temperature (Tg)			
TMA	°C		IPC TM-650 2.4.24
DSC	°C	170	IPC TM-650 2.4.25
Decomposition Temperature (Td)			
Initial	°C	351	IPC TM-650 2.3.41
5%	°C	368	IPC TM-650 2.3.41
T260	min	>60	IPC TM-650 2.4.24.1
T288	min	>60	IPC TM-650 2.4.24.1
T300	min	28	IPC TM-650 2.4.24.1
CTE (X,Y)	ppm/°C	6-9	IPC TM-650 2.4.41
CTE (Z)			
< Tg	ppm/°C	99	IPC TM-650 2.4.24
> Tg	ppm/°C	259	IPC TM-650 2.4.24
z-axis Expansion (50-260°C)	%	3.5	IPC TM-650 2.4.24
<b>3. Mechanical Properties</b>			
Peel Strength to Copper (1 oz/35 micron)			
After Thermal Stress	lb/in (N/mm)	3.6 (0.6)	IPC TM-650 2.4.8
At Elevated Temperatures	lb/in (N/mm)	3.6 (0.6)	IPC TM-650 2.4.8.2
After Process Solutions	lb/in (N/mm)	3.6 (0.6)	IPC TM-650 2.4.8
Young's Modulus	Mpsi (GPa)	2.0 (13.8)	IPC TM-650 2.4.18.3
Flexural Strength	kpsi (MPa)	38 (262)	IPC TM-650 2.4.4
Tensile Strength	kpsi (MPa)	5 (35)	IPC TM-650 2.4.18.3
Compressive Modulus	kpsi (MPa)		ASTM D-695
Poisson's Ratio	-		ASTM D-3039
<b>4. Physical Properties</b>			
Water Absorption (0.062")	%	0.3	IPC TM-650 2.6.2.1
Specific Gravity	g/cm <sup>3</sup>	1.38	ASTM D792 Method A
Thermal Conductivity	W/mK	0.2	ASTM E1461
Flammability	class	V-0	UL-94

Results listed above are typical properties, provided without warranty, expressed or implied, and without liability. Properties may vary, depending on design and application. Arlon reserves the right to change or update these values.

## Availability:

Arlon Part Number	Glass Style	Resin %	Mil/Ply	Flow %
55NT147	E210	49	1.7	12
55NT247	E220	49	2.9	12
55NT347	E230	49	3.8	12
55NT153	E210	53	1.8	15
55NT253	E220	53	3.1	15
55NT353	E230	53	4.1	15

## Recommended Process Conditions:

Process inner-layers through develop, etch, and strip using standard industry practices. Use brown oxide on inner layers. Adjust dwell time in the oxide bath to ensure uniform coating. Bake inner layers in a rack for 60 minutes at 107°C - 121°C (225°F - 250°F) immediately prior to lay-up. Vacuum desiccate the prepreg for 8 - 12 hours prior to lamination.

### Lamination Cycle:

- 1) Pre-vacuum for 30 - 45 minutes
- 2) Control the heat rise to 4.5°C – 6.5°C (8°F – 12°F) per minute between 82°C and 138°C (180°F and 280°F)

Panel Size		Pressure	
in	cm	psi	kg/cm <sup>2</sup>
12 x 12	30 x 40	250	17
12 x 18	30 x 46	275	19
16 x 18	41 x 46	350	25
18 x 24	46 x 61	400	27

- 3) Product temperature at start of cure = 182°C (360°F).
- 4) Cure time at temperature = 90 minutes
- 5) Cool down under pressure at ≤ 6°C/min (10°F/min)

De-smear using alkaline permanganate or plasma with settings appropriate for epoxy; plasma is preferred for positive etchback

Conventional plating processes are compatible with 55NT

Standard profiling parameters may be used; chip breaker style router bits are not recommended

Bake for 1 - 2 hours at 121°C (250°F) prior to solder reflow or HASL

# 55NT

**Arlon Electronic Materials...**  
**CHALLENGE US!**

For samples, technical assistance and customer service, please contact Arlon Electronic Materials Division at the following locations:

**NORTH AMERICA:**

Arlon EMD, 9433 Hyssop Drive, Rancho Cucamonga, CA  
Tel: (909) 987-9533 • Fax: (909) 987-8541

**FRANCE:**

CCI Eurolam  
9, rue Marcelin Bertholet  
92160 Antony, France  
Phone: (33) 146744747  
Fax: (33) 146666313

**ISRAEL:**

Tech Knowledge, Ltd.  
159 Yigal Alon Street,  
Tel Aviv 6744367, Israel  
Phone: (972) 36958117  
Fax: (972) 36917117

**CHINA:**

Zack Peng  
Room 6A, Unit 2, Bldg 2  
Jin Cheng Shi Dai, Tian Road  
Shenzhen, China 518103  
Phone: (86) 75528236491  
Fax: (86) 75528236463

**GERMANY:**

CCI Eurolam  
Otto-Hahn-Str. 46  
63303 Dreiech Germany  
Phone: (49) 610339920  
Fax: (49) 6103399229

**ITALY:**

Dralmi, SAS  
Via Cellini 5  
20129 Milano Italy  
Phone: (39) 025460507  
Fax: (39) 0255013199

**JAPAN:**

Nakao Corp.  
12-8 Nihonbashi Hisamatsu-Cho  
Tokyo 103-0005 Japan  
Phone: (81) 336623201  
Fax: (81) 336617118

**UK & SCANDINAVIA:**

CCI Eurolam – UK  
Ulness Walton Lane  
Leyland, PR26 8NB, UK  
Phone: (44) 1772452236  
Fax: (44) 1772456859